



# 大榮工業股份有限公司

## Great Winexpress Industrial (Holdings) Company Limited

香港上環文咸東街79-85號文咸中心901室  
Room 901, Bonham Centre,  
79-85 Bonham Strand East,  
Central, Hong Kong.

Tel : 2545 6068 2541 1114 (5 Lines)  
Fax : 2854 0404 2544 3157  
E-mail : greatwin@hkstar.com

### Technical Data Sheet

#### BIAX 600/300

##### Specification 技术参数

| Construction<br>结 构           | Area Weight<br>单位面积质量,g/m <sup>2</sup> | Tolerance<br>偏差范围, %              | Remark<br>备注                        |
|-------------------------------|----------------------------------------|-----------------------------------|-------------------------------------|
| 0°                            | 2                                      | --                                | Roving:E-GLass 巨石<br>68*1Z22-766(X) |
| +45°                          | 301                                    | ±5.0                              | Roving:E-GLass 巨石<br>600-386H       |
| 90°                           | 2                                      | --                                | Roving:E-GLass 巨石<br>68*1Z22-766(X) |
| -45°                          | 301                                    | ±5.0                              | Roving:E-GLass 巨石<br>600-386H       |
| Mat 短切层                       | 300                                    | ±7.0                              | Roving::巨石 2400-520                 |
| Stitching 缝编线                 | 10                                     | ±5.0                              | Polyester 83dtex/36F                |
| Total Area Weight<br>总单位面积质量  | 916                                    | ±7.0                              |                                     |
| Stitch Gauge 针密度: 6Gauge/25mm |                                        | Stitch style 针法: 10-10            |                                     |
| Stitch length 缝编长度: 2.78mm    |                                        | Width 宽度: ±10mm                   |                                     |
| Moisture Content 含水率: ≤0.2%   |                                        | Loss on Ignition 可燃物含量: 0.5%~4.0% |                                     |

##### Packing 包装

Product is manufactured in form of a roll wound on a paper tube and then packed in a plastic film and placed within woven bag on pallet. 产品生产时卷于纸芯管上，然后用塑料薄膜包装，置于编织袋中，采用托盘装。Above package is standard one, any other package style is negotiable by both of us.此包装为一般情况，包装方式可由供需双方协商而定。

##### Storage 贮存

It is recommended that the fiber glass are stored in a cool and dry environment. Recommended temperature range of storage is between 10 ~ 30°C and relative humidity between 50 ~ 75%. The fiber glass should remain in the packaging until just prior to use.

推荐玻璃纤维产品存放在通风干燥的环境中。贮存温度范围建议为 10~30℃之间，相对湿度为 50~75%。产品在使用前，需保持包装完好状态。

注 Remark: Other specification is available upon request 以上参数仅表明此系列产品的一般情况，对于正式定单，各参数以客户确认为准。