



大榮工業股份有限公司

Great Winexpress Industrial (Holdings) Company Limited

香港上環文咸東街79-85號文咸中心901室
Room 901, Bonham Centre,
79-85 Bonham Strand East,
Central, Hong Kong.

Tel : 2545 6068 2541 1114 (5 Lines)
Fax : 2854 0404 2544 3157
E-mail : greatwin@hkstar.com

E-BIAX 600 ($\pm 45^\circ$)

Specification 技术参数

Construction 结 构	Area Weight 单位面积质量,g/m ²	Tolerance 偏差范围,%	Remark 备注
0°	2	--	E-GLass 68dtex
+45°	301	± 5.0	E-GLass 300TEX
90°	2	--	E-GLass 68dtex
-45°	301	± 5.0	E-GLass 300TEX
Mat 短切层	--	--	
Stitching 缝编线	8	± 5.0	Polyester 83dtex
Total Area Weight 总单位面积质量	614	± 5.0	
Stitch Gauge 针密度: 6Gauge/25mm		Stitch style 针法: 10-10	
Stitch length 缝编长度: 2.8mm		Width 宽度: ± 10 mm	
Moisture Content 含水率: $\leq 0.2\%$		Loss on Ignition 可燃物含量: 0.5%~4.0%	

Packing 包装

Product is manufactured in form of a roll wound on a paper tube and then packed in a plastic film and placed within woven bag on pallet. 产品生产时卷于纸芯管上，然后用塑料薄膜包装，置于编织袋中，采用托盘装。Above package is standard one, any other package style is negotiable by both of us.此包装为一般情况，包装方式可由供需双方协商而定。

Storage 贮存

It is recommended that the fiber glass are stored in a cool and dry environment. Recommended temperature range of storage is between 10 ~ 30°C and relative humidity between 50 ~ 75%. The fiber glass should remain in the packaging until just prior to use.
推荐玻璃纤维产品存放在通风干燥的环境中。贮存温度范围建议为 10~30°C 之间，相对湿度为 50~75%。产品在使用前，需保持包装完好状态。

注 Remark: Other specification is available upon request 以上参数仅表明此系列产品的一般情况，对于正式定单，各参数以客户确认为准。